

PLASKOLITE, INC.

See Thru and First Surface Mirror Finish Specifications

Issue Date: 3/10/2001

Revision Date: 12/11/2009

Page 1 of 1

Approval: David Beickelman

Characteristic	Specification
Scratches	
Under .060"	Acceptable
.060" – .500"	1 per sq. ft.
Over .500"	None
Pits and Speckles	
Under .020"	Acceptable
.020" – .049"	8 per sq. ft.
.050" – .065"	3 per sq. ft.
.066" - .100"	1 per sq. ft.
Over .100"	None
Black Specks	
Under .020"	Acceptable
.020" – .029"	6 per sq. ft.
.030" - .065"	3 per sq. ft.
.066" - .100"	1 per sq. ft.
Over .100"	None
Coating Debris and Fibers	
Under .030"	Acceptable
.030" – .060"	3 per sq. ft.
.061" - .100"	1 per sq. ft.
Over .100"	None
Splatter, Voids, White Spots	
Under .020"	Acceptable
.020" to .065"	2 per sq. ft.
.066" - .100"	1 per sq. ft.
Over .100"	None

*Visual Inspection